

DESCRIPTION

Backing			NT	MK
Design			Wood	
Thickness	ISO 24346	mm	2.25 ± 0.15	6.2 ± 0.30
Weight	ISO 23997	kg/m ²	2.70 ± 0.15	3.65 ± 0.30
Roll width		cm	200 (-0 +1)	196
Roll length		lm	24	15

PERFORMANCE

Dimensional stability	ISO 23999 ASTM D 1204	%	≤ 0.3	≤ 0.3
Abrasion resistance	TABER ISO 9352	mg	≤ 300	
Indentation test	ISO 24343-1	mm	≤ 0.2	≤ 1.0
Low temperature resistance	D 42 1235 A	°C	- 20	
Thermal conductivity	ISO 22007-2	W/mK	0.089	
Colour fastness	ISO 877/76 ISO 4582/80 ASTM D 4459		≥ 6	
Fire resistance	FMVSS 302		Conform	
	ASTM E648	W/cm ²	Class 1	
	R118-2		Conform	
Resistance to chemicals	ISO 26987	-	Unaffected by diluted acids and bases Unaffected by domestic products (excluding solvents for plasticized PVC)	